

ALLOYS

TYPE	ALLOYS	COMPANY	COMPOSITION % BY MASS								
			AU	Pt	Pd	Ag	Cu	Sn	Zn	In	Ga
Yellow high noble	Bioplatinlloyd	BEGO	75.1	7.8	-	14.8	-	-	1.8	-	-
	Biopontostar XL	BEGO	86.0	11.5	-	-	-	-	1.8	x	-
White high noble Noble	Begostar	BEGO	54.0	-	26.5	15.5	-	2.4	-	1.4	-
	Begopal	BEGO	2.0	-	73.0	-	13.5	5.0	-	5.0	1.4
Yellow high noble	Platinlloyd 100	BEGO	72.0	3.9	-	15.5	-	-	-	-	-
	Gold EWL H	BEGO	2.0	-	27.5	58.5	11.0	9.0	-	1.0	-
Cobalt base	Wirobond 280 Wironium plus	BEGO BEGO	Co	Cr	W	Mo	Ga				
			60.2	25.0	6.2	4.8	2.9				
			62.5	29.5	-	5.0	-				